

4207-A1 Milgen Road, Columbus, GA 31907

706-940-0049

www.texttest.com

TexTesT Report: 7365
Date: 11/5/18
Page: 1 of 1

CLIENT: **NATIONAL FIREPROOFING INC.**
420 Wagner Road
Porter, IN 46304

Attn: Vincent J. Hoffman

SAMPLE IDENTIFICATION: FLAMEX-PF Treatment on
Woven Fabric 50% Cotton/50% Polyester
End Use: Drapery Interior

12.2 oz./sq.yd.

AS RECEIVED

CALIFORNIA STATE FIRE MARSHALL
FLAME RESISTANCE
TITLE 19, SECTION 1237.1
SMALL SCALE TEST


		AFTER FLAME (Seconds)	AFTER GLOW (Seconds)	CHAR LENGTH (Inches)
SPECIMEN	1W	0.0	0.5	3.0
	2W	0.0	0.5	2.9
	3W	0.0	0.5	2.9
	4W	0.0	0.5	2.5
	5W	<u>0.0</u>	<u>0.5</u>	<u>3.1</u>
		0.0	0.5	2.9
	6F	0.0	0.5	2.5
	7F	0.0	0.5	2.9
	8F	0.0	0.5	2.9
	9F	0.0	0.5	2.7
	10F	<u>0.0</u>	<u>0.5</u>	<u>3.1</u>
		0.0	0.5	2.8

CRITERIA: PASS/FAIL

CHAR: 6.0" Max. Ind.
AFTER FLAME: 4.0 Seconds Max. Avg. each direction

COMMENTS: The submitted sample passes the requirements of California State
Fire Marshall 1237.1 Flame Resistance Small Scale Test, as received.

TEXTTEST


signed by

Lab Technician: G.T. Flame Log G55405